

## BÜFA®-SWIM-NPG-GELCOAT-H

ISO/NPG gelcoat, brushing quality

Prod. No. 753-9999

**Product description** BÜFA® SWIM NPG Gelcoat H 753-9999 is a pre-accelerated gelcoat in a brushing consistence and is base on an unsaturated ISO/NPG polyester resin dissolved in styrene.

**Applications** BÜFA® SWIM NPG Gelcoat H 753-9999 is suitable for swimming pools which are always subjected to high chemical, thermal and hydrolytic loads. The shades of colours are specially tested according to the AVK chlorine test (enclosure 2 of the Producer Guideline for GRP Swimming Pools, section 6) for chemicals that are used for the treatment of water in private households but not treatment with gaseous chlorine or ozone.

Specifications / technical data	Property	Test method	Value	Unit
	Density at 20 °C	DIN 53 217/2	ca. 1,2	g/ml
	Viscosity at 20 °C Brookfield RV/DV-II Spl 4 rpm 4	ISO 2555	20 000 - 25 000	mPas
		ISO 2555		mPas
	Styrene content		33 - 36	%
	Flash point	DIN 53 213	+ 32	°C

**Curing**

**Reactivity:**  
**BÜFA method in accordance with DIN 16 945 6.2.2.1**  
 (100 g gelcoat + 2 ml Butanox M-50)

20 - 30 °C	12 - 20 min
20 °C - Tmax	28 - 40 min
Tmax	140 - 180 °C

**Gel time at 20 °C in a 100 g cup with 2 ml Butanox M-50:** 12 - 20 min

### Attention!

The information given above refers exclusively to the use of the catalyst named and the quantity specified. The use of different products or differing quantities may yield different results.

# BÜFA®-SWIM-NPG-GELCOAT-H

ISO/NPG gelcoat, brushing quality

Prod. No. 753-9999

## Directions for use

Our release agent system BF 500 /BF 700 has been tested and successfully used with this gelcoat. Before using other release agents, they should be tested for suitability under practical conditions.

If circumstances permit, we recommend post-curing the moulded part for several hours at 80 °C to achieve optimal gelcoat properties.

For more information on working and curing, see the notes in our Technical Information leaflet, "Working with OLDOPAL Gelcoats".

## Storage/Handling

This product must be stored cool in closed containers, protected from sunlight. Shelf-life is at least 3 months in unopened, original containers stored up to a temperature of 20 °C. Gel and curing times may change with increasing duration of storage.

Note: The Information given above is based on our current state of knowledge and experience. In view of the many factors that may influence working conditions and the application of our products, the user is not relieved from carrying out his own tests and experiments. No legally binding warranty of certain properties or suitability for a particular purpose can be derived from this information. It is the responsibility of the receiver or user of our products to observe proprietary rights as well as existing laws and regulations. The latest version of the corresponding EU Safety Data Sheet must also be observed.

BÜFA Gelcoat Plus GmbH & Co. KG  
Hohe Looge 2-8  
26180 Rastede  
GERMANY  
Phone +49 4402 975-0  
Fax +49 4402 975-300  
gelcoatplus@buefa.de  
www.buefa.de  
www.buefagelcoatplus.com

A member of the BÜFA-Group