

Product Data Sheet

Synolite 5750-A-3

Chemical/physical nature

Synolite 5750-A-3 is a DCPD based, pre-accelerated, non-thixotropic, unsaturated polyester resin in styrene monomer.

Major applications

It is designed for general casting applications and can be used specifically for shower tray casting behind a gelcoat or primed ABS capped acrylic.

Principal properties

Synolite 5750-A-3 is a resilient resin with controlled exotherm. It is characterised by its high filler acceptance and rapid cure rate.

Product specifications

Property	Range	Unit	TM
Viscosity, 23°C	170 - 190	Pa.s	2013
Solids content, IR	63.5 - 66.5	%	2033
Gel time from 25 to 35°C	8.5 - 9.5	minutes	2625
Cure time from 25°C to peak	12.5 - 16.5	minutes	2625
Peak temperature	120 - 140	°C	2625
Cure time from 35°C to peak	Max 6.5	minutes	2625

Remarks

TM 2013: spindle Z2, speed 100 s-1, program
TM 2026: 1% in Butanox M50

Properties of the liquid resin (typical values)

Property	Value	Unit	TM
Stability, no init., dark,	3	months	-
Flash point	32	°C	2800

Properties of cast unfilled resin (typical values)

Property	Value	Unit	TM
Tensile strength	40	MPa	ISO 527-2
Tensile E-modulus	3.3	GPa	ISO 527-2
Elongation at break	1.5	%	ISO 527-2
Flexural strength	80	MPa	ISO 178
Flexural E-Modulus	3.0	GPa	ISO 178
Heat Deflection Temp. (HDT)	82	°C	ISO 75-A
Hardness Barcol 934.1	42	Barcol	2604

Casting cured overnight at ambient and post-cured for 2 hrs at 90°C.

Guidelines before use

Before use, the resin should be conditioned at a well defined, application dependant temperature (usually 15°C minimum for a MEKP / Co cure). Stir the product before blending.

Storage guidelines

The resin should be stored in the original, unopened and undamaged packaging, in a dry place at temperatures between 5°C and 30°C. Shelf life is reduced at higher temperatures. The shelf life of styrene containing unsaturated polyesters will be significantly reduced when exposed to sunlight. Store in dark and in 100% light tight containers only. With DCPD resins there is a tendency for skin formation if exposed to air. Whilst products are formulated to reduce this characteristic, exposure to air and ventilation in bulk storage facilities should be minimised.

Material Safety

A material safety data sheet for the product is available on request.

Test methods

Test methods (TM) referred to in the table(s) are available on request.

The user is held to check the quality, safety and other properties of the product referred to herein. The information and recommendations in this document are to the best of our knowledge, reliable. However, no rights whatsoever can be derived from this document or the information contained therein by any party, other than those expressly accepted by a selling entity of the Royal DSM group of companies ("DSM Selling Entity") in a binding sale and purchase agreement for product referred to herein. For the avoidance of doubt THE ROYAL DSM GROUP OF COMPANIES MAKE NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR PURPOSE. Unless explicitly agreed to otherwise in writing by the DSM Selling Entity, all offers, quotations, sales and deliveries of DSM products are subject to the General Conditions of Sale of such DSM Selling Entity.

This document has been issued by DSM Composite Resins on behalf of the DSM Selling Entity. For more information: www.compositeresins.com