


**CUROX® M-312R**

## Technical Data Sheet - Thermosets - Ketone peroxides (Ambient temperature)



Chemical Name	Methylethyl ketoneperoxide
CAS-No.	1338-23-4
Properties	Liquid mixture, red coloured

**Description**

Red coloured, mobile liquid, consisting of peroxides based on methyl ethyl ketone, essentially desensitised with aliphatic ester. This ketone peroxide is used as an initiator (radical source) in the curing of unsaturated polyester resins.

Special advantages: Due to the red coloured peroxide, homogenisation in the resin can be controlled and after curing the red colour disappeared. High efficiency with special preaccelerated and stabilized resin types.

Main application: curing of moulded parts at ambient temperature in combination with cobalt accelerators.

**Technical Data**


Property	Characteristics / Value
Appearance	red coloured liquid
Active oxygen	ca. 8.6 - 9.1 % w/w
De-sensitising agent	aliphatic ester
Density at 20°C	ca. 1.01 g/cm <sup>3</sup>
Viscosity at 20°C	ca. 13 mPas
Miscibility	immiscible with water, miscible with ester, alcohol
Critical temperature (SADT)	>50 °C
Cold storage stability	liquid to below -25 °C
Recommended storage temperature	below 30 °C
Storage stability (activity) as from date of delivery	6 months

## CUROX® M-312R

### Technical Data Sheet - Thermosets - Ketone peroxides (Ambient temperature)

#### Activity:

"Cobalt Curing" after DIN 16945 at 25°C with OPA resin (20g in a test tube)						
Formulation (parts by weight)						
Medium reactive resin type (OPA)	100	100	100	100	100	100
CUROX® M-312R	2	2	2	2	1	1
Accelerator COB-1TX	2	1	0.5	0.2	1	0.5
Curing data						
Gel time $t_{gel}$ [min]	3.5	4.5	8.5	26.0	13.5	24.0
Curing time $t_{max}$ [min]	17.0	19.0	25.0	53.5	40.0	59.5
Peaktemperature $T_{max}$ [°C]	139	141	137	115	109	93



**CUROX® M-312R****Technical Data Sheet -Thermosets - Ketone peroxides (Ambient temperature)****Application****POLYESTER CURING:**

Curing agent for all UP resin types at ambient temperature in combination with cobalt accelerators. Standard dosage level: 1-3% as supplied, with 0.2-2% of a 1% cobalt solution.

"Shelf life" (gel time of resin + peroxide) usually only a few hours, depending on temperature and resin type.

"Pot life" (gel time of resin + peroxide + accelerator) relatively short, but may be prolonged by adding Inhibitor TC-510. Thus, the mould release factor (fMR = tMR/tgel) can be improved considerably.

**CURING PERFORMANCE:**

Moderate evolution of heat. Relatively long mould release time, moderate mould release factors. Temperatures below 20°C prolong curing times considerably, alternatively cobalt / amine accelerators should then be used.

**PROCESSING METHODS:**

Particularly hand lay-up, spray lay-up, centrifugal casting, filament winding, casting of resins, and surface coatings (putties, fillers, gelcoats and topcoats).

**SPRAY EQUIPMENT:**

Use spray equipment in accordance with manufacturer's instructions. Ensure all safety devices are operational. Do not clear gun by spraying MEKP into the air.

This information and all further technical advice – whether verbal, in writing, by way of trials - are reflecting our present knowledge and experience based on internal tests with local raw materials with the purpose to inform about our products and applications. The information should not be construed as guaranteeing specific properties of products described or their suitability for a particular application, nor as providing complete instructions for use. The information implies no guarantee for product and shelf life properties, nor any liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. We reserve the right to make any changes according to technological progress or further developments.

Application and usage of our products based on our technical advice is out of our control and sole responsibility of the user. The user is not released from the obligation to conduct careful inspection and testing of incoming goods in order to verify the suitability for the intended application.