

# Chemlease® One FS EZ

## Semi-Permanent Release Agent

### Description

Chemlease® One FS EZ is a HAP's-free\* solvent-based semi-permanent releasant for the composites industry which affords easy application in one step. The product should be applied to the mold surface *very lightly* and allowed to dry. The original mold surface finish appearance will be reproduced once the product is dry.

\* HAPs are not formula constituents of this product. Standard manufacturing processes may result in trace quantities [ $<0.1\%$ ] of HAPs.

### Application - Wipe-on method

1. The mold surface must be cleaned to remove all traces of wax, release agents, and other sealers before application of Chemlease® One FS EZ can be attempted. Use Chemlease® Mold Cleaner EZ.
2. Apply a light, even coat to the mold surface. As a guide to achieving a "light coat" when the film is applied to a **VERTICAL** mold surface, the wet film should shine, but there should be no runs in it. Runs in the film indicate too heavy an application.
3. As soon as the wiping action appears not to be forming a film, add more product to the cloth as describe above in step #2.
4. Continue working across the mold until its entire surface has been coated.
5. Allow the film to dry for 15 minutes.
6. Using the same procedure, apply 5 complete coats. For a new mold or difficult to release part, apply an additional 2 coats for a total of 7 coats.
7. Cure for a minimum of 30 minutes after the final coat has been applied.
8. Begin molding and continue until release-ease appears tight.
9. When release becomes difficult reapply 1 coat of Chemlease® One FS EZ. Allow to cure for 15 minutes and resume molding.

### Application - Spray-on method

1. The mold surface must be cleaned to remove all traces of wax, release agents, and other sealers before the application of Chemlease® One FS EZ can be attempted. Use Chemlease® Mold Cleaner EZ
2. Use an HVLP spray gun to apply a light, even coat to the mold surface. As a guide to achieving a "light coat" when the film is applied to a **VERTICAL** mold surface, the wet film should shine, but there should be no runs in it. Runs in the film indicate too heavy an application.
3. Keep the spray gun 20- 26 cm away from the mold surface while spraying approximately 0.6 meter<sup>2</sup> per second. We recommend 0,5 - 1,1 bar for the fluid pressure and 1,4 – 2,1 bar for the air pressure as a general guideline.

4. Apply 5 coats one after another. No waiting between coats is necessary. For a new mold or difficult to release part, apply an additional 2 coats for a total of 7 coats.
5. After last coat is applied, allow 30 minutes for cure before gel coating. Begin molding.
6. When release becomes difficult reapply 1 coat of Chemlease® One FS EZ. Allow to cure for 15 minutes and resume molding.

### Important

The recommended number of coats and cure times are a general guideline found to be more than sufficient in a broad spectrum of molding conditions. When molding products with extreme geometries or experiencing low-humidity conditions in the shop, the customer may find the need to extend the cure time between coats and increase the number of coats applied to the mold. The efficiency of a release film is best determined through a combination of tape tests and experimentation.

### Storage

Do not store at temperatures above 50°C. Keep container tightly sealed to prevent evaporation and/or contamination. If stored in cold temperatures allow warming to room temperature before using.

### Handling

We believe Chemlease® One FS EZ has a low degree of hazard when used as intended. For more information, request a copy of Chem-Trend's Material Safety Data Sheet.

### Packaging

Chemlease® One FS EZ is available in containers filled with 0,68 kg, 3,4 kg, 13,7 kg and 148 kg.

### Further Information

Request information on our complete range of materials for this industry.

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. Chem-Trend warrants only that its products will meet its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. Users are requested to check that they are in possession of the latest version of this document and Chem-Trend is at their disposal to supply any additional information.

Edition 10.04.2012